



Technical Data



	Standard	Result	Product	Size (inch)	Slip Resistance		
					BS7976 (dry)	BS7976 (wet)	DIN 51130
Thickness		3.0 mm (1/8")	VG1-7	48" x 7"	61	33	R10
Size		See separate table	VG5-7	48" x 7"	61	33	R10
Wear layer		0.5 mm (20 mil)	VGW33T	48" x 7"	61	33	R10
Warranty	Commercial	15 years*	VGW39T	48" x 7"	61	33	R10
	Residential	Lifetime*	VGW40T	48" x 7"	61	33	R10
Beveled edge		No	VGW41T	48" x 7"	61	33	R10
Standards	ASTM F1700		VGW42T	48" x 7"	61	33	R10
Classification	ASTM F1700	Class III Type B	VGW44T	48" x 7"	61	33	R10
Reaction to fire	ASTM E648-06	Class 1	VGW49T	48" x 7"	61	33	R10
Flammability test	FF 1-70; Federal Approval	Pass	VGW50T	48" x 7"	61	33	R10
Slip resistance	ASTM C1028	ADA compliant	VGW51T	48" x 7"	61	33	R10
		Dry 0.68	VGW53T	48" x 7"	61	33	R10
		Wet 0.66	VGW54T	48" x 7"	61	33	R10
	BS 7976	See separate table	VGW70T	48" x 7"	61	33	R10
DIN 51130	See separate table	VGW71T	48" x 7"	61	33	R10	
Staining resistance	ASTM F925	Pass	VGW76T	48" x 7"	61	33	R10
Light fastness	ASTM F1515	Pass	VGW81T	48" x 7"	61	33	R10
		$\Delta E = 3.3$	VGW85T	48" x 7"	61	33	R10
Abrasion resistance	ASTM D3884	115,000 cycles	VGW86T	48" x 7"	61	33	R10
Dimensional stability	ASTM F2199	Pass	VGW89T	48" x 7"	61	33	R10
		-0.002"/lin.ft	VGW91T	48" x 7"	61	33	R10
Static load	ASTM F970	1,000 psi	VGW92T	48" x 7"	61	33	R10
Flexibility	ASTM F137	Pass	VGW93T	48" x 7"	61	33	R10
Adhesive		K-91A	VGW94T	48" x 7"	61	33	R10
		DrySet	VGW95T	48" x 7"	61	33	R10
		K-Spray	VGW96T	48" x 7"	61	33	R10
		Karndean Epoxy	VGW97T	48" x 7"	61	33	R10
Recycling		Suitable	VGW98T	48" x 7"	61	33	R10
			VGW99T	48" x 7"	61	33	R10
			VGW100T	48" x 7"	61	33	R10
			VGW101T	48" x 7"	61	33	R10
			VGW102T	48" x 7"	61	33	R10

*Subject to terms

For more information:
 Call: 888-266-4343
 Email: info@karndean.com
 Visit: www.karndean.com

Manufactured to:

